Caov-3

300319

GENERAL INFORMATION

Description

□□□ Caov-3 □□□ 54 □□□
adenocarcinoma □□□
□□□ □□□ 1976 □□□
□□□
□□□ □□□ Caov-3 □□□
□□□ □□□ □□□
□□□ □□□
□□□
□□□ □□□
□□□-□□□ Caov-3 □□□
□□□
□□□ □□□ □□□ Caov-3 □□□
□□□ □□□ NB/70K, CA-125, Ba-2 □□□ Ca-1 □□□
□□□
□□□ Caov-3 □□□
□□□ □□□ □□□ nonsense □□□ p53 □□□
□□□ □□□ PIK3CA □□□ □□□
□□□ □□□ □□□ Caov-3 □□□
□□□
□□□, □□□ □□□ □□□ □□□
□□□ Caov-3 □□□ □□□
□□□ □□□
□□□ □□□ □□□ □□□
Caov-3 □□□ 3 □□□
□□□
□□□ □□□
□□□ □□□ □□□
□□□ □□□ □□□
□□□ 78 □□□

Tissue	□□□
Disease	□□□ □□□

Synonyms

- CaOv-3
- CaOV-3
- CAOV-3
- CAOV3
- CaOV3
- CaOv3
- Caov3
- CA-OV-3

CLASSIFICATION

Organism	Human

Sex	Female
Growth properties	Adherent
Biosafety level	1

CHARACTERISTICS

Morphology	ลักษณะคล้าย □ยื่อบุผิว

IDENTIFIERS

Citation

Caov-3 (หมาย □ลบแคตตาล็อก Cytion 300319)

NCBI TaxID	9606
Cellosaurus	[CVCL_0201]()

EXPRESSION AND SUSCEPTIBILITY

Isoenzymes

AK-1, 1, ES-D, 1, G6PD, B, GLO-I, 1-2, Me-2, 2, PGM1, 1, PGM3, 1

HANDLING AND CULTURE

Culture medium

DMEM, w: 4.5 กรัม /ลิตร กลูโคส , w: 4 มิลลิโมลาร์ แอล -กลูตามีน , w: 3.7 กรัม /ลิตร NaHCO3, w: 1.0 มิลลิโมลาร์ โซ □ดียมไพรู □วต (หมาย □ลขบทความ Cytion 820300a)

Incubation atmosphere	37°C, 5%CO2, บรรยากาศชื้น

Supplements

□ติมอาหาร □ลี้ยง □ชื้อด้วย FBS 10%

Dissociation reagent	TrypLE Express 10 นาที □□□ 37°C

Subculturing

น□าอาหาร □ลี้ยง □ซลล์ □ก่าออกจาก □ซลล์ที่ □กาะติดและล้างด้วย PBS ที่ไม่มีแคล □ซียมและแมกนี □ซียม □□□หรับขวด T25 ให้ใช้ PBS 3-5 มล . และ □□□หรับขวด T75 ให้ใช้ 5-10 มล . จาก □□□นปิด □ซลล์ให้มิดด้วย Accutase โดยใช้ 1-2 มล . สำ□หรับขวด T25 และ 2.5 มล . สำ□หรับขวด T75ปล่อยให้ □ซลล์บ่มที่อุณหภูมิห้อง □ป็น □วลา 8-10 นาที □พื่อให้ □ซลล์หลุดออกจากกัน หลังจากบ่มแล้ว ให้ผสม □ซลล์ □บา ๆ กับอาหาร □ลี้ยง □ซลล์ 10 มิลลิลิตร □พื่อทำให้ □ □ซลล์แขวนลอยอีกครั้ง จากนั้นปั่น □หวี่ยงที่ 300 □ท่าของแรงโน้มถ่วงโลก (300xg) □ป็น □วลา 3 นาที □ทส่วนใสที่ได้ทิ้งไป แล้วแขวนลอย □ซลล์ในอาหาร □□◌ี □ยง □ซลล์ใหม่ จากนั้นถ่าย □ซลล์ไปยังขวด □พาะ □□□□ยงใหม่ □◌ี □□ติมอาหาร □□□□ยง □ซลล์ใหม่ไว้แล้ว

Cytion GmbH
Nikola-Tesla-Str. 3
69124 Heidelberg
Tel: +49 (0)6221 405780
info@cytion.com
cytion.com

Registered office Heidelberg
VAT ID: DE283292917
Local court Mannheim - HRB 714394
CEO / Geschäftsführer: Jonathan Steubing

Banking information
Sparkasse Heidelberg
IBAN: DE35 6725 0020 0009 2076 86
BIC: SOLADES1HDB

2 / 4

Thawing and culturing

Confirm that the vial remains deeply frozen upon delivery, as cells are shipped on dry ice to maintain optimal temperatures during transit.
Upon receipt, either store the cryovial immediately at temperatures below -150°C to ensure the preservation of cellular integrity, or proceed to step 3 if immediate culturing is required.
For immediate culturing, swiftly thaw the vial by immersing it in a 37°C water bath with clean water and an antimicrobial agent, agitating gently for 40-60 seconds until a small ice clump remains.
Perform all subsequent steps under sterile conditions in a flow hood, disinfecting the cryovial with 70% ethanol before opening.
Carefully open the disinfected vial and transfer the cell suspension into a 15 ml centrifuge tube containing 8 ml of room-temperature culture medium, mixing gently.
Centrifuge the mixture at 300 x g for 3 minutes to separate the cells and carefully discard the supernatant containing residual freezing medium.
Gently resuspend the cell pellet in 10 ml of fresh culture medium. For adherent cells, divide the suspension between two T25 culture flasks; for suspension cultures, transfer all the medium into one T25 flask to promote effective cell interaction and growth.
Adhere to established subculture protocols for continued growth and maintenance of the cell line, ensuring reliable experimental outcomes.

QUALITY CONTROL AND CRYOPRESERVATION

Sterility

[illegible] PCR [illegible]
[illegible]

Freeze medium	[illegible] ([illegible] FBS) + 10% DMSO [illegible] CM-1 ([illegible] Cytion 800100) [illegible]

Storage conditions

[illegible] −150 [illegible] −196 °C [illegible] −80 °C [illegible]

Shipping conditions

[illegible] −78 °C [illegible]

DONOR

Donor age	54 [illegible]
Ethnicity	[illegible]

LEGAL AND SAFETY

Safety precautions

[illegible]

Warranty

□□□Cytion □□
□□□
60 □□□□□□□□□□□□□□□□□□□□□□□□□□□□□
□□□
□□□□□□□□□□□□□□□□□□□ □□□/□□□□□□□□□□□□□□□□□□□□□□
□□□□□□□□□□□□□□□□□□□□□□□□□ □□□□□□□□□□
<a href=""/Who-we-are/Warranty/"" hreflang=""x-default"">□□□□□□□□□□□□□□□□□□.

Material Transfer Agreement required	Yes